



P.O. BOX 939  
Cuyahoga Falls, OH 44223, U.S.A.

## Technical Data Sheet

Contact Us: Phone: 330-923-7070  
Fax: 330-923-4005  
E-mail: [eagle1@eagleelastomer.com](mailto:eagle1@eagleelastomer.com)  
Web: [www.eagleelastomer.com](http://www.eagleelastomer.com)

# COMPOUND#: EE30475B

**Description:** 75 durometer black AFLAS fluoroelastomer compound.

**Application Temperatures:** High Temp: 400° F ( 204° C)

### Compound Information:

- **% Fluorine:** 57%
- **Cure System:** Peroxide
- **Color:** Black
- **Compounded for:** Molding:(Compression, Injection, Transfer) and Extrusion.
- **Form** Slab, Strip, Pre-form or Calendered Sheet.
- **Storage** Preserves best when stored in a cool/dry environment. Rheometer retesting suggested @ 6 months.
- **Cured Products** O-Ring Cord, Profiles, Sheet, and Tubing
- **Stock** Yes

### Typical Rheological Properties:

Conditions: MDR .5 ARC 6 minutes @ 370° F (188° C) Per ASTM D-6204.

- **Min torque:** 1.34 **Inch/lbs.**
- **Max torque:** 7.66 **Inch/lbs.**
- **Scorch Ts1:** 0.60 **Minutes.**
- **Cure Tc90:** 2.60 **Minutes.**

### Typical Physical Properties:

▪ Conditions: Press cured 10 minutes @ 370° F (188° C) and Post cured for 16 hours @ 480° F (250 °C).

- **Tensile Strength** (Per ASTM D-412): 1550 **PSI** ( 10.7 **Mpa**)
- **100% Modulus** (Per ASTM D-412): 750 **PSI** (5.2 **Mpa**)
- **Ultimate Elongation** (Per ASTM D-412): 355 **%**
- **Shore A Hardness** (Per ASTM D-2240): 76 **Pts.**
- **Specific Gravity** (Per ASTM D-297): 1.61 (**H2O=1**)
- **Compression Set** (Per ASTM D-395): 31.88 **%** CONDITIONS: 22 hrs@ 392 °F (200°C)

### Compounded to Meet:

This information is based on tests performed by Eagle Elastomer, Inc. and vendors that we believe are reliable. Your results may vary due to differences in equipment, test types or conditions. It is intended for persons having technical skill and at their own discretion or risk. You must evaluate and determine whether this compound is suitable for your intended application.

**AS9100 with ISO 9001 with Design  
Approval Certificate Number: 95.072  
MANUFACTURED IN THE U.S.A.**