



P.O. BOX 939 Cuvahoga Falls. OH 44223. U.S.A. Contact Us: Phone: 330-923-7070

Fax: 330-923-4005

E-mail: <u>eagle1@eagleelastomer.com</u>
Web: <u>www.eagleelastomer.com</u>

COMPOUND#: EE94475H

Description: 75 durometer black Viton™ GLTS fluoroelastomer compound.

Application Temperatures: High Temp: 400 °F (205 °C)

Low Temp: Dynamic: -22°F (-30°C) Static: -49°F (-45°C)

Compound Information:

% Fluorine: 64%Cure System: PeroxideColor: Black

Compounded for: Injection, Transfer, Compression Molding and Extrusion
 Form: Slab, Strip, Calendered Sheet, or Extruded pre-form

• Storage: Preserves best when stored in a cool/dry environment. Rheometer retesting suggested @ 6 months.

Typical Rheological Properties:

Conditions: MDR .5° ARC 3 minutes @ 370°F (188°C) Per ASTM D-6204

Min torque: 2.10 Inch/lbs.
Max torque: 24.29 Inch/lbs.
Scorch Ts1: 0.30 Minutes
Cure Tc90: 0.69 Minutes

Typical Physical Properties:

- Conditions: Press cured 10 minutes @ 370°F (188°C) and Post cured for 16 hours @ 480°F (250°C).

■ Tensile Strength (Per ASTM D-412): 2700 PSI (18.6MPa)
■ 100% Modulus (Per ASTM D-412): 800 PSI (5.5MPa)

Ultimate Elongation (Per ASTM D-412): 250 %
 Shore A Hardness (Per ASTM D-2240): 77 Pts.
 Specific Gravity (Per ASTM D-297): 1.84 (H2O=1)

• Compression Set (Per ASTM D-395): 20 % Conditions: 22 hrs@ 392 °F (200 °C)

Compounded to Meet:

ASTM D-2000 Call out: M4HK 714 A1-11 B38 EF31 EO78 F17 Z1 = 75 +/- 5 Duro

This information is based on tests performed by Eagle Elastomer, Inc. and vendors that we believe are reliable. Your results may vary due to differences in equipment, test types or conditions. It is intended for persons having technical skill and at their own discretion or risk. You must evaluate and determine whether this compound is suitable for your intended application.

Viton™ is a trademark of The Chemours Company FC, LLC, used under license by Eagle Elastomer, Inc.

